

IN THE CLAIMS

Please cancel claims 16 and 31-36 without prejudice or disclaimer and amend the remaining claims as follows.

1-13. Previously Cancelled

~~14.~~ (Currently Amended) A transfer apparatus comprising a bag, said bag comprising a film having a thickness of 4 to 6 mils, said film comprising:

a metallocene catalyzed an olefinic base resin in an amount of 99.4-99.5% by weight of said film;

an amide-based antistatic agent in a range of from 0.1 to 0.5% by weight of said film; and

an amine-based antistatic agent in a range of from 0.01 to 0.1% by weight of said film;

and

the balance of said film being a filler comprising diatomaceous earth;

wherein said the amide-based antistatic agent comprises N,N-bis(2-hydroxyethyl)dodecanedamide and said the amine-based antistatic agent comprises POE(2) C13-C15 alkylamine and said film has a surface resistivity of less than 1×10^{11} ohms per square and a charge decay of less than 3.5 seconds.

15. Previously Cancelled

16. CANCELLED

17-24. Previously Cancelled

~~25.~~ (Previously Amended) A transfer apparatus according to claim ~~14~~, wherein the proportions of said olefinic base resin, amide-based antistatic agent, amine-based antistatic agent and filler are selected such that said film passes a discharge incendivity test.

26-27. Cancelled

²28. (Currently Amended) An apparatus for transporting pharmaceuticals ~~without~~ with exposing workers to the health hazards of the pharmaceuticals, said apparatus comprising a bag, said bag comprising ~~including~~ a film, said film comprising:

a metallocene-catalyzed an olefinic base resin in an amount of 99.4-99.5% by weight of said film;

an amide based-antistatic agent in a range of from 0.1 to 0.5% by weight of said film; and

an amine-based antistatic agent in a range of from 0.01 to 0.1% by weight of said film; and

the balance of said film being a filler comprising diatomaceous earth;

wherein the amide-based antistatic agent comprises N,N-bis(2-hydroxyethyl)dodecanamide; and the amine-based antistatic agent comprises POE(2) C13-15 alkylamine and said film has a surface resistivity of less than 1×10^{11} ohms per square and a charge decay of less than 3.5 seconds; and

a pharmaceutical, disposed within the bag.

¹29. Previously Cancelled

⁴30. (Currently Amended) An apparatus according to claim ~~28~~³, wherein said olefinic base resin is a metallocene ~~metallocene~~-catalyzed resin; and the filler is diatomaceous earth.

[31-36. CANCELLED

⁵31. (New) The apparatus of claim ~~28~~³, wherein the bag is heat sealed with the pharmaceutical inside.